

## tesa® 4952

### Double-sided PE-foam mounting tape

tesa® 4952 is a double sided PE foam tape, consisting of a highly conformable closed cell PE-foam backing and a tackified acrylic adhesive. The foam tape offers a highly versatile adhesive for high immediate adhesion on numerous types of substrates and high immediate bonding strength even at low bonding pressure. tesa® 4952 features excellent resistance to water, UV and ageing, making it completely suitable for outdoors. The double sided foam tape is capable of compensating different thermal expansions of different materials. tesa® 4952 features very good cold shock absorption. tesa® 4952 is ideally used for constructive mounting applications and has been externally certified for mirror mounting.

tesa® 4952 has been externally tested and certified for mirror mounting by the LGA institute. Report number IWQ FSG 329 1189. The tape has an immediate peel adhesion: foam splitting on steel, aluminium, ABS, PC, PS, PET, PVC. And a peel adhesion after 14 days: foam splitting on steel, aluminium, ABS, PC, PS, PET, PVC.

### Main Application

- tesa® 4952 is used for constructive mounting applications
- The foam tape is used for furniture mirror mounting
- The double sided tape is used for the mounting of car mirrors
- tesa® 4952 is used for mounting functional trims & profiles
- tesa® 4952 is used for the mounting of decorative panels in the interior fitout industry

### Technical Data

▪ Backing material	PE foam	▪ Tensile strength	10 N/cm
▪ Color	white	▪ Type of liner	glassine
▪ Total thickness	1150 µm	▪ Colour of liner	brown
▪ Type of adhesive	tackified acrylic	▪ Thickness of liner	70 µm
▪ Elongation at break	200 %	▪ Weight of liner	80 g/m <sup>2</sup>

### Adhesion to

▪ Steel (initial)	6.5 N/cm	▪ Steel (after 14 days)	8.0 N/cm
▪ ABS (initial)	5.0 N/cm	▪ ABS (after 14 days)	8.0 N/cm
▪ Aluminium (initial)	5.0 N/cm	▪ Aluminium (after 14 days)	8.0 N/cm
▪ PC (initial)	5.0 N/cm	▪ PC (after 14 days)	8.0 N/cm
▪ PE (initial)	2.7 N/cm	▪ PE (after 14 days)	2.8 N/cm
▪ PET (initial)	5.0 N/cm	▪ PET (after 14 days)	7.0 N/cm
▪ PP (initial)	2.8 N/cm	▪ PP (after 14 days)	5.5 N/cm
▪ PS (initial)	5.0 N/cm	▪ PS (after 14 days)	7.5 N/cm
▪ PVC (initial)	5.0 N/cm	▪ PVC (after 14 days)	8.0 N/cm

For latest information on this product please visit <http://l.tesa.com/?ip=04952>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

## tesa® 4952

### Double-sided PE-foam mounting tape

#### Properties

▪ Temperature resistance short term	80 °C	▪ Resistance to chemicals	●●●
▪ Temperature resistance long term	80 °C	▪ Softener resistance	●●
▪ Tack	●●●	▪ Static shear resistance at 23°C	●●●
▪ Ageing resistance (UV)	●●●	▪ Static shear resistance at 40°C	●●●
▪ Humidity resistance	●●●●		

Evaluation across relevant tesa® assortment: ●●●● very good ●●● good ●● medium ● low

#### Additional Information

tesa® 4952 has been tested and approved by LGA institute for mirror mounting. Report number IWQ FSG 329 1189.

##### Peel Adhesion:

- immediately: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC

For latest information on this product please visit <http://l.tesa.com/?ip=04952>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.