# productinformation

# tesa® ACX<sup>plus</sup> 7078

ACX<sup>plus</sup> High Resistance 2000μm

tesa® ACX<sup>plus</sup> 7078 is a black acrylic foam tape. It consists of a high-performance acrylic system and due to its unique components it combines a very good temperature resistance with an outstanding cold shock resistance. It is designed for demanding outdoor bonding applications especially in combination with the tesa Adhesion Promoters. The visco-elastic, foamed acrylic core compensates different thermal elongation of bonded parts.

## Main Application

Bonding of panels and reinforcement bars in the following Industries:

- Solar
- Elevator
- Production Equipment
- Transportation

#### Technical Data

Backing material	foamed acrylic		Type of adhesive	pure acrylic
Color	deep black	•	Elongation at break	1000 %
Total thickness	2000 um			

#### Adhesion to

	Steel (initial)	16.0 N/cm	Steel (after 3 days)	40.0 N/cm
•	Aluminium (initial)	14.0 N/cm	Aluminium (after 3 days)	32.0 N/cm
	Glass (initial)	24.0 N/cm	Glass (after 3 days)	40.0 N/cm

### **Properties**

•	Temperature resistance short term	220 °C		Resistance to chemicals	• • • •
	Temperature resistance long term	120 °C		Softener resistance	• •
	Tack	• •		Static shear resistance at 23°C	•••
	Ageing resistance (UV)	•••		Static shear resistance at 70°C	•••
٠	Humidity resistance	••••	٠	T-block	••••
Ev	aluation across relevant tesa® assortment:	: ••• very good	• •	● good ● ● medium ● low	

#### Additional Information

PV 22 = White PE coated paper liner tesa® ACX<sup>plus</sup> branded PV 24 = Blue filmic liner

For latest information on this product please visit http://l.tesa.com/?ip=07078

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchatability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 1 of 1 - as of 25/05/2017 - enau